

PROPELLER BLADES FOR "METEOR"

\*\*\*\*\*

is made at Vickers Terni Works, Spezia on October 22nd 1924.

\*\*\*\*\*

Large N°.	Tensile Strength Kg./mm <sup>2</sup>	Elongation per cent
*****	*****	*****
985	48.9	32
967	49.7	26
973	47.7	28
979	49.6	20 End Break
973	48.5	32
966	46.65	16 End Break
967	48.9	20 " "

B- The diameter of each test piece was 13.5 m/m and the elongation taken on a length of 50 m/m.

Surveyor to Lloyd's Register . -



© 2021

Lloyd's Register  
Foundation