



S.S. GONCALO VELHO"

Nº 75162 - REG. BR.

Nº 2. INTERM. SHAFT.

MARK ON SHAFT.

LLOYD'S

Nº 3402

14/1/13

H. C. F.

TEST TAKEN

TENSILE FLONG. BEND.

1 Nº 1

34.7 kg.

$\frac{1}{2}$

25.4%

180°

good

Nº 2


33.8 kg.

$\frac{1}{2}$

21.4%

145°

broken.

Friedrich 

Hamburg Report Nr. 24124