

ESSEL'S NAME TEXACO 171 Report N. YK. No. 37381

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in _____ of an inch.

STRAKE.	AMIDSHIP.					FORWARD.				AFT.				REMARKS.
	Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.	Original Thickness.	Thickness by drilling.		Diminution if any.	
		Port.	Std.	Port.	Std.		Port.	Std.			Port.	Std.		
PAIR SHEER STRAKE														
Strake below														
MAIN SHEER STRAKE50	.44	.46	.06	.04									
at Strake below40	.34	.37	.06	.03									
2nd " "38	.31	.34	.07	.04									
3rd " "38	.34	.34	.04	.04									
4th " "38	.34	.34	.04	.04									
5th " "38	.37	.34	.01	.04									
6th " "56.	.47.		.09										
7th " "														
8th " "														
9th " "														

Drillings at ends to be made in the vicinity of the peak bulkheads.

© 2020

Lloyd's Register
Foundation

008137.008145-0209