

S. #41C

COPY

of Hakodate.

8th March, 1925.

Z. Sato,

to Nippon Seikoso & Co., on the 19th January and 21st February, 1925,
examining one shaft bracket manufactured by them for the order of
Messrs Mitsubishi Nagasaki-Kosenaho and on inspection found to be, as
far as could be ascertained, sound and free from defects.

The test pieces for Tension & Bending were taken each from both ends.
The tensile strength and elongation found to be as follows:-

Marked No.	Tensile strength Tons Per Sq Inch.	Elongation in 2 Inches.	Article.
101023	30.6	34.5	Shaft bracket.
---	30.6	35.3	---"---

The bend tests good.

The drop and percussive tests good.

The shaft bracket were examined in casting, partly rough turned and
found to be satisfactory.

Fee Yen 150.00.
Expense Yen 70.00.

Assistant Registrar
Lloyd's Register.



© 2021

Lloyd's Register
Foundation

008158-008167-0318