

NAME

TANGARA

Report *Rio de Janeiro* No. 5209

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in 20s of an inch.

	AMIDSHIP.						FORWARD.						AFT.						REMARKS.	
	Original Thickness.		Thickness by drilling.		Diminution if any.		Original Thickness.		Thickness by drilling.		Diminution if any.		Original Thickness.		Thickness by drilling.		Diminution if any.			
	Port.	Std.	Port.	Std.			Port.	Std.	Port.	Std.			Port.	Std.	Port.	Std.				
RAKE O	14	14	14				11	11	11				11	11	11					
N	13	7	7	6			12	12	12				12	10	10	2				
M	12	11	11	1			9	9	9				9	9	9					
RAKE L	13	7	7	6			10	10	10				10	10	8		2			
K	12	7	7	5			9	9	9				10	9	8	1	2			
J	13	7	11	6	2		10	10	10				10	10	10					
H	13	9	9	4			10	10	10				10	9	10	1				
G	14	11	11	3			13	11	11	2			11	10	11	1				
F	13	10	11	3	2		10	10	10				-							
E	13	10	10	3			12	11	10	1	2		-							
D	12	10	11	2	1								9	9	9					
C	13	11	11	2			10	5	10				10	10	10					
B	12	11	11	1			9	7	6	2	3		9	9	9					
A	14	12	12	2			13	12	12	1			13	12	12					

Drillings at ends to be made in the vicinity of the peak bulkheads.

The plate underlined ■ was renewed in drydock.

008186-008200-0280