

U.S.S.R. *Loadline Certificate as amended*  
 VESSEL'S NAME *SS "KOMSOLOLSK"* Report *ROTTERDAM* No. *30008*

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in

*mm* of an inch.

STRAKE.	AMIDSHIP.						FORWARD.						AFT.						REMARKS.
	Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.					
		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.				
# BRIDGE SHEER STRAKE.	12 1/2	12 1/2	12 1/2														Examination of shell plating found good inside and outside; edges and butts not inspected.  J. van der Noel.  Rotterdam 14 July 1967.		
Strake below.....																			
SHEER STRAKE	14	14	14			15	15	15			10	10	10						
1st Strake below	14	14	14			23	23	23			17	17							
2nd " "	12 1/2	12	12	1/2	1/2	23	23	23			19 1/2	15	15						
3rd " " BULGE	12 1/2	12 1/2	12 1/2			23	23				14	14							
4th " "	C																		
5th " "	B																		
6th " "	A																		
7th " "	4.2																		
8th " "																			
9th " "																			
10th " "																			
11th " "																			
12th " "																			

Drillings at ends to be made in the vicinity of the peak bulkheads.