

South Durham Steel & Iron Company Limited,


West Hartlepool, 15th May 1925

LTS OF TESTS FOR

S. S. "Lima" (Messrs Irvine's D.D. Coy.).

Cast No.	Descript'n	ORIGINAL			ULTIMATE STRESS		FRACTURED				Extension Per Cent.	Remarks
		Width	Thick- ness	Area	Total	Per Sq. Inch of Original Area	Width	Thick- ness	Area	Difference Area Per Cent		
ake (shell).		1.49	.66	.984	27.6	28.1					20	
" (")		"	.74	1.102	30.5	27.6					19	
is		1.49	.79	.432	13.5	31.2					12	

bold & temper bends satisfactory



© 2021

Lloyd's Register
Foundation

008434-008438-0147