

# FORTUN STELLA

## Report

WILL BE  
FORWARDED <sup>NO.</sup>

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

## DECIMALS

The thicknesses are in \_\_\_\_\_ of an inch.

STRAKE.	AMIDSHIP.						FORWARD.						AFT.						REMARKS.
	Original Thickness.		Thickness by drilling.		Diminution if any.		Original Thickness.		Thickness by drilling.		Diminution if any.		Original Thickness.		Thickness by drilling.		Diminution if any.		
	Port.	Std.	Port.	Std.	Port.	Std.	Port.	Std.	Port.	Std.	Port.	Std.	Port.	Std.	Port.	Std.	Port.	Std.	
ELTER	76	75	75	.01	.01	.44	.51	.50	✓	✓	.44	.41	.40	.03	.04	DRILLINGS AMIDSHIPS TAKEN IN RESERVE BUNKER (No. 3 HOLD). END DRILLINGS TAKEN IN HOLDS IN VICINITY OF PEAK BULKHEAD			
AT SHEER STRAKE	.66	.67	.67	✓	✓	.44	.55	.51	✓	✓	.44	.44	.41	✓	.03				
STAKE BELOW	.62	.57	.57	.05	.05	.44	.50	.40	✓	.04	.44	.44	.47	✓	✓				
SECOND AT SHEER STRAKE	.64	.55	.53	.09	.11	.44	.36	.40	.08	.04	.44	.44	.45	.03	✓				
BELOW	.64	.53	.46	.11	.18	.44	.40	.40	.04	.04	.44	.40	.52	.04	✓				
STRAKE BELOW	.64	.49	.49	.15	.15	.44	.40	.50	.04	✓	.44	.40	.40	.04	.04	© 2020 Lloyd's Register			
" "						.48	.50	.50	✓	✓	.48	.38	.38	.10	.10				
" "						.48	.50	.47	✓	.01	.48	.45	.38	.03	.00				
" "						.48	.38	.40	.10	.08	.48								
" "																			
UPPER STRUCTURES	.40	.44				.40	.40				.38	.40				15.0.			
" "																			

Drillings at ends to be made in the vicinity of the peak bulkheads.

© 2020

13/12/89

008993-009003-0017