

NAME

Slavija

Report

No.

ESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in *mm* of an inch.

	AMIDSHIP.					FORWARD.					AFT.					REMARKS.
	Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		
		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.	
AKE .....																
AKE .....	✓ 10	9.5	10	.5	-	7.5	8	7			7.5	8	8			
	7.5	8	7	-	.5	6.5	6	6.5			6.5	8	7			
	7.5	8	8			6.5	7	7			6.5	6	6			
	7.5	9	8			6.5	6	9			6.5	6	6			
	7.5	com.				6	com.				6	com.				
	7.5					7.5					7.5					
														</		

Drillings at ends to be made in the vicinity of the peak bulkheads.

original thickness as stated above are correct.

RKM  
18.10.22.

009743-009756-0392