EL'S NAME "MERKURY" REPORT No.

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in hundredths of an inch.

RAKE.		AMIDSHIP. Original Thickness mm	Thickness by drilling. Port. mm	Thickness by drilling. Std. mm	Diminution if any. Port. mm	Diminution if any. Std. mm	FORWARD. Original Thickness. mm	Thickness by drilling. Port. mm	Thickness by drilling. Std. mm	Diminution if any. Port. mm	Diminution if any. Std. mm	AFT. Original Thickness. mm	Thickness by drilling. Port. mm	Thickness by drilling. Std. mm	Diminution if any. Port. mm	Diminution if any. Std. mm	REMARKS.
																	appd.
HEER		—					—										
		—					—										10-7/16
RAKE	G	17.4	13.5	ren.d	3.9	—	12.7	12.5	11.3	0.2	1.4	12.7	11.0	14.1	1.7	—	above Rule H.
below	F	9.5	10.0	8.2	—	1.3		8.0	11.0				ren.d	10.0			6/16
"	E	11.1	11.4	9.8	—	1.3		8.8	9.3/8.8				10.5/7.6/8.5	9.3/8.9			9-6/16
(fwd)	D	9.5	9.5	9.1	0.0	0.4		8.9	9.2				11.0/9.1/10.0	10.0			6/16
"	C	9.5	cement		—	—		10.8	10.0				10.0	cement		—	6/16
"	B	9.5		cement	—	—		11.7			—				—	—	6/16
(and)	A	11.1			—	—	11.1	11.5		—	—	11.1			—	—	7/16
"				Bar	Keel												
"																	
"																	
"																	
"																	
"																	
"																	

Drillings at ends to be made in the vicinity of the peak bulkheads.

010004- 010011- 0130

© 2021 Lloyd's Register Foundation