

EL'S NAME

'Mercury'

REPORT

Left Rotterdam

No.

2/8/82

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in hundredths of an inch.

For Office use only.

TRAKE.	AMIDSHIP.						FORWARD.						AFT.						REMARKS.
	Original Thickness	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.					
		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.				
ESHEER KE																		⊗ Renewed.	
below																		Rules. (1948)	
STRAKE	G	62	53	9	-	43	49	44	-	-	43	43	55	-	-			.49 - .34	
ke, below	F	37	39	32	-	5	37	31	43	6	-	37	39	-	-			.38 - .34.	
"	E	43	45	39	-	4	37	35	35	2		37	30	35	7	2			
"	D	37	37	35	-	2	37	35	35	2	2	37	35	39	2	-			
"	C	37	6mm		-	-	37	42	39	-	-	37	39	C	-	-			
"	B	37	-	-	-	37	45	C	-	-	37	6mm		-	-				
"	A	43	-	-	-	43	45	C	-	-	43	-	-	-	-		.44 - .40.		
"																			
"																			
"																			
"																			
"																			
"																			
"																			

Drillings at ends to be made in the vicinity of the peak bulkheads.

© 2021

Lloyd's Register Foundation

010004-010011-0131