

Rpt. 6.

For the information of Surveyors and the Committee only.

Received at

Office,

10

Lloyd's Register of Shipping.

(Report on Vessel No. *110*)

Port *Vancouver.*

No. *260*

SHIP FORGINGS OR CASTINGS.

I have to report that the undermentioned ~~Iron~~ Steel Forgings ~~or~~ Castings, manufactured by *Burns Dry Dock Co.* of *N. Vancouver* for the Vessel No. *110*, being built by *Burns Dry Dock Co.* of *N. Vancouver.* have been inspected by me as set forth below and found to be, so far as can be seen, *sound & free from defects.*

Mark on Forgings ~~or~~ Castings.

Lloyd's

No. *260*

14.5.26 A.S.

A. Scott.

18.5.26. Vancouver.

STERN FRAME.

RUDDER FRAME.

STEM.

Material*

A.S.

How made

forged & machined

Dimensions

to drawing

Progress on Inspection

Complete.

Date when Inspected

8.5.26. 14.5.26

CASTINGS.

Tests on Standard Test Pieces.

Tensile Test—

Tons per square inch

30.4

Extension per cent.

27.5

Cold Bending Test—

Angle before fracture

180° without fracture.

Drop Test—

Height from ground

Hammering Test—

If made according to Rules and found satisfactory

SKETCHES OF FRAMES SHOWING POSITION AND DESCRIPTION OF WELDS OF FORGINGS.

Fee (if any chargeable) £

To be paid at

Charged.

* If of Iron, state whether scrap or puddled Iron. If of steel, state whether made on the Open Hearth process.

See 11.16. T.

010219-010228-0150

inner surfaces *drawn out.*

Is there a drain arrangement fitted at the lowest part of each