

# Lloyd's Register of Shipping.

(Report on Machinery, No. 1191 Port Malmö)

The words FORGINGS or CASTINGS should be struck out if may be required.

No. 1723. ENGINE FORGINGS ~~OR CASTINGS~~.

I have to report that the Forgings ~~or castings~~, as herein described, manufactured by Messrs. The Skoda Works Ltd. of Pilsen for the Engines No. \_\_\_\_\_ being constructed by \_\_\_\_\_ of \_\_\_\_\_ for the Ship No. MS. 171, being built by Messrs. Kockums Mek. Verkstad of Malmö have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to Malmö.

Mark on Forgings or Castings.

Lloyd's  
No. 8959. JK  
HK. 21.5. 1931.

Prague, 26th May 1931.

*Hans Kolbow.*

	CRANK SHAFT.	<del>ENGINE</del> SHAFT. <u>Crank</u>	INTERMEDIATE SHAFT.	TUBE SHAFT.  SCREW SHAFT.
Material* ...	<u>Annealed Siemens Martin IngSteel.</u>			
How made ...	<u>forged</u>	<u>forged</u>		
If Annealed...	<u>Annealed</u>	<u>Annealed.</u>		
Dimensions, Forgings	<u>to Drawing No: 64188.</u>			
Weight, Castings ...				
Progress on Inspection }	<u>finished</u>	<u>finished</u>		
Tests on Standard Test Pieces.				
Tensile Test— Tons per square inch	<u>48.0</u> <u>48.6</u>	<u>44.8</u> <u>47.3</u>		
Extension per cent	<u>36.0</u> <u>37.0</u>	<u>37.0</u> <u>37.0</u>		
Cold Bending Test— Angle before fracture	<u>180 degrees, satisfactory.</u>			
Dates when Inspected	<u>30. 1; 13. 2; 20. 2; 27. 2; 21. 5.</u>			

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

Fee (if any chargeable) £

To be paid at Prague.

\* If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.

