

For the information of Surveyors and the Committee only.

Received at \_\_\_\_\_ Office, \_\_\_\_\_ 19

# Lloyd's Register of Shipping.

Order: 957  
Est: 30976

(Report on Machinery, No. 1191 Port Malmö)

No. 2686 ENGINE FORGINGS OR CASTINGS.

I have to report that the Forgings ~~or castings~~, as herein described, manufactured by Messrs. Borsigwerk, A.G. of Borsigwerk for the Engines No. \_\_\_\_\_ being constructed by Messrs. Kockums mek. Verkstads of Malmö for the Ship No. MS 171, being built by \_\_\_\_\_ of \_\_\_\_\_

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to Messrs. Kockums mek. Verkstads A.B. of Malmö

Forgings ~~or castings~~

Vienna, 20th October 1930

Lloyd's  
No. 4332

688/89

(HS 17-10-30 STAMPED ON SHFTS)

	2 CRANK SHAFTS	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT.
	<del>XXXXXXXXXXXX</del>			SCREW SHAFT.
Material	Siem. Mart. Ing. Steel			
Condition	forged			
Heat Treatment	annealed			
Dimensions, Forgings	155 Ø			
Dimensions, Castings	- - -			
Surface Finish	finished			
Conformity with Standard Test Pieces.				
Tensile Test—	31.1 27.6			
per square inch				
Elongation per cent	29.5 31.6			
Bending Test—				
angle before fracture	180 degrees good			
When Inspected	25.9; 16.10.30			

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

(if any chargeable) £

To be paid at

© 2021  
VIENNA

\* If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.

010236.010245.0044



For the information of Surveyors and the Committee only.

# Lloyd's Register of Shipping

Ref: 957  
Ref: 30976

## ENGINE FORGINGS

to report that the forgings ~~XXXXXXXXXX~~ of Messrs. Borsigwerk, A.G. being constructed by Messrs. Kockums mek. Verkestaðs Main 6 for the ship No. 171, being built by Messrs. Kockums mek. Verkestaðs A.B. of Main 6 have been inspected by me as set forth below, and found to be as good as new, sound and free from defects. These have been despatched to


V i e n n a, 20th October 1930

4332 688/89

CRANK SHAFTS	THRUST SHAFT	INTERMEDIATE SHAFT	TUBE SHAFT
XXXXXXXXXXXX			SCREW SHAFT
Stem. Mart. Ing. Steel			
Forged			
annealed			
155 0			
---			
finished			
31.1 27.6			
29.5 31.6			
180 degrees Good			
25.9; 16.10.30			

PARTICULARS OR OTHER TESTS APPLIED TO CASTINGS.

VIENNA



© 2021

Lloyd's Register  
Foundation

