

Rpt. 7.

For the information of Surveyors and the Committee only.

London Report No. 24107.

Received at

Office,

19

Lloyd's Register of Shipping.

(Report on Machinery, No.

Port

No. 17791

ENGINE FORGINGS OR CASTINGS.

I have to report that the Forgings or Castings, as herein described, manufactured by The Old Park Ld. of Sheffield

for the ^{VARJ} ~~Engines~~ No. 249/4 being constructed by Jessup, Crabtree & Co. Ld. of Gt. Yarmouth for the Ship No. 249, being built by

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to

rk on Forgings or Castings

Lloyd's

No. 1739

R.N.F. 11/5/29

R.W. Fawcett

Sheffield

15/5/29

	CRANK SHAFT.	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT.
	FLYWHEEL SHAFT.			(Spare)
erial* ...				SCREW SHAFT.
v made ...				Siemens Steel
annealed...				Forged
ensions, Forgings				Yes
ght, Castings ...				Dia 5 1/2"
gress on { nspection }				
orecasts on Standard Test Pieces.				Black Forging
ile Test—				8642/1
ons per square inch ...				32.8
xtension per cent ...				28.0
Bending Test—				188°
ngle before fracture ...				8/5/29 to 11/5/29
s when Inspected				

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

Spore for S. P. Angel

(if any chargeable) £

To be paid at

If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.

9.27.

010766-010776-0075

The foregoing is a correct description,