

VESSEL'S NAME

LIVERPOOL MARU

REPORT

No.

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in hundredths of an inch.

STRAKE.	AMIDSHIP.								FORWARD.				AFT.				REMARKS.
	Original Thickness	Thickness by drilling.		Diminution if any.		Original Thickness	Thickness by drilling.		Diminution if any.		Original Thickness	Thickness by drilling.		Diminution if any.			
		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		
RIDGE SHEER STRAKE	Q	19.	19.				10.	10.				10.	11.				
Ridge Strake below	N	18	14.	18.			12	12.	12.			10	11.	12.			
SHEER STRAKE	M	<del>18</del>	16.	16.5	2	1 1/2	<del>13</del>	13.	13.			<del>13</del>	13.	14.			
Strake below	L	<del>16</del>	16.5	16.	"	"	"	14.	13.			"	14.	14.			
"	J	17	15	12.	2	4	"	12.	12.			"	10.	10.			
"	H	"	-	14	-	3	"	13.	13.			"	11.	11.			
"	G	"	16.5	16.	"	1	"	16.	11.			"	11.	11.			
"	F	"	16.5	16.5	"	"	13	14.	14.			13	12.	12.			
(B.L.G.)	E	17	15.	14.5	2	3	<del>12</del>	12.	12.			<del>12</del>	11.5	12.			
"	D	17	16.	14.5	1	3	"	14.	14.			"	14.	14.			
"	C	"	14.5	14.5			"					"					
"	B	"	15	15			"					"					
"	A	"	15	15			"	12.5	12.5			"	14.	14.			
KEEL	27	25.					16.5.					16.					
"	27						19					19					

Drillings at ends to be made in the vicinity of the peak bulkheads.

011062-011070-0094