

GLASGOW REPORT No. 54392

F 4465

Waitaki

54156

Lloyd's Register of Shipping.

RESULTS OF TESTS OF STEEL. SHAFTS

e by MESSRS. WILLIAM BEARDMORE & CO., LTD., GLASGOW,

MESSRS. ALEX. STEPHEN & SONS, LTD., LINTHOUSE, GLASGOW, ENG. No. 538,

SHIP No. 538

Test Batch No.	No. of Pieces.	Description.	Charge Mark.	Sample No.	diameter Thickness.	Area.	Tons per square inch.	Extension on 3 inches.	% BEND
602/3	2	Coupling Ends			.798	.50	30.4	31	180°
604/5	2	- ditto -			"	"	31.0	31	"
606/7	2	- ditto -			"	"	30.8	31	"
608	1	- ditto -			"	"	30.4	32	"
509/10/ 511/12	4	Crank Pins			"	"	30.0	31	"
809	1	Interim Shaft			"	"	30.2	34	"
810	1	- ditto -			"	"	30.8	32	"
811	1	- ditto -			"	"	30.4	27	"
812	1	- ditto -			"	"	30.0	28	"
813	1	Prop. Shaft			"	"	30.4	28	"
814	1	- ditto -			"	"	30.8	27	"
959	1	Thrust Shaft			"	"	31.4	27	"

Chas. S. Porter

Glasgow. 14/11/1933



© 2020

Lloyd's Register
Foundation

011079-011088-0077