

EL'S NAME

Molitebo

REPORT

NNS

No. 6497

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in hundredths of an inch.

STRAKE.	AMIDSHIP.						FORWARD.				AFT.				REMARKS.			
	Original Thickness	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.				
		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.		Std.		
GE SHEER																		
LAKE																		
Below																		
STRAKE	K	98	99	96	-	2	50	89	91	-	-	50	92	98	-	-		
Below	J	83	84	74	-	9	50	79	78	-	-	50	84	75	-	-		
	H	66	60	61	6	5	50	54	58	-	-	50	58	60	-	-		
	G	66	64	65	2	1	50	55	56	-	-	50	65	61	-	-		
	F	66	58	65	8	1	66	64	61	2	5	50	64	65	-	-		
Belge	E	75	70	75	5	-	66	69	68	-	-	62	69	69	-	-		
	D	76	67	62	9	14	66	70	60	-	6	62	75	67	-	-		
	C	76	73	75	3	1	66	65	64	1	8	62	68	64	-	-		
	B	76	73	70	3	6	66	67	68	-	-	62	63	61	-	1		
	A	76	66	74	10	2	66	68	65	-	1	62	58	65	-	-		
Keel		86	86	-			86	78		8		86	75		9			

Drillings at ends to be made in the vicinity of the peak bulkheads.

Lloyd's Register  
Foundation

011823-011825-0092