

Screwshaft ^M/_S "NOR STRAUM"

LLOYD'S REGISTER OF SHIPPING

RESULTS OF TESTS OF STEEL

Made by Messrs. Colvilles Ltd., Motherwell.

For Messrs. P. Eriksen, Bergen, Norway.

2 Bar
Nos.

Order No. X.1719 of 7/12/53.

BSEA 9865 of 17/12/53.

Mild Steel Round Bars

10.2.54.	Book 401 6/32	1	7 $\frac{1}{4}$ " dia. Bars F.4464	51	.564 dia. .250	30.8	34	51
15.2.54.	5/52	2	6 $\frac{1}{2}$ " dia. Bars G.3710	138	.564 dia. .250	31.6	32	137/138
22.2.54.	3/73	4	3" dia. Bars G.3732	383	1.00 dia. .785	31.6	37 on 4"	1/383 3/384
25.2.54.	3/80	2	6" dia. Bars G.3724	498	1.00 dia. .785	29.8	38 on 4"	2/498
26.2.54.	3/95	3	3 $\frac{1}{4}$ " dia. Bars A.606	598	1.00 dia. .785	31.3	35 on 4"	598, 599, 600
1.3.54.	7/95	2	5" dia. Bars V.910	542	1.00 dia. .785	30.5	36 on 4"	2/542
" " "	"	2	" " " G.3716	543	1.00 dia. .785	30.5	32 on 4"	2/543
" " "	8/98	3	5 $\frac{1}{4}$ " dia. Bars F.4487	682	1.00 dia. .785	31.4	36 on 4"	3/682
2.3.54.	Book 402 10/6	12	5 $\frac{1}{2}$ " dia. Bars A.639	860	1.00 dia. .785	31.2	30 on 4"	4/860, 4/861, 4/865.

31 Rounds Machining Quality

PROPELLER ANSEL

0087 1/2

10.2.54.	Book 401 6/32	1	7 $\frac{1}{4}$ " dia. Bars F.4464	51	.564 dia. .250	30.8	34	51
15.2.54.	5/52	2	6 $\frac{1}{2}$ " dia. Bars G.3710	138	.564 dia. .250	31.6	32	137/138
22.2.54.	3/73	4	3" dia. Bars G.3732	383	1.00 dia. .785	31.6	37 on 4"	1/383 3/384
25.2.54.	3/80	2	6" dia. Bars G.3724	498	1.00 dia. .785	29.8	38 on 4"	2/498
26.2.54.	3/95	3	3 $\frac{1}{4}$ " dia. Bars A.606	598	1.00 dia. .785	31.3	35 on 4"	598, 599, 600
1.3.54.	7/98	2	5" dia. Bars V.910	542	1.00 dia. .785	30.5	36 on 4"	2/542
" " "	"	2	" " " G.3716	543	1.00 dia. .785	30.5	32 on 4"	2/543
" " "	8/98	3	5 $\frac{1}{4}$ " dia. Bars F.4487	682	1.00 dia. .785	31.4	36 on 4"	3/682
2.3.54.	Book 402 10/6	12	5 $\frac{1}{2}$ " dia. Bars A.639	860	1.00 dia. .785	31.2	30 on 4"	4/860, 4/861, 4/865.

31 Rounds Machining QualityBend Tests Satisfactory.

© 2021

Lloyd's Register
Foundation

011947-011954-0087 1/2

011947-011954-0091 1/2