

17 APR 1930

Received at \_\_\_\_\_ Office, \_\_\_\_\_ 19

# Lloyd's Register of Shipping.

(Report on Machinery, No. \_\_\_\_\_ Port \_\_\_\_\_)

## No. 20740 ENGINE FORGINGS OR CASTINGS.

I have to report that the Forgings or Castings, as herein described, manufactured by The Old Park Forge Ltd. of Sheffield for the Engines No. 2641/4 being constructed by Incesses Plenty & Sons Ltd. of Hewbury for the Ship No. \_\_\_\_\_, being built by \_\_\_\_\_ of \_\_\_\_\_

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to \_\_\_\_\_

Report on Forgings or Castings.

RW Fawcett  
Sheffield  
2/4/30

Lloyd's  
No. 3470  
R.N.F. 28/3/30

	<del>CRANK SHAFT.</del>	<del>THRUST SHAFT.</del>	<del>INTERMEDIATE SHAFT.</del>	<del>TUBE SHAFT.</del>
	<del>FLYWHEEL SHAFT.</del>			<del>SCREW SHAFT.</del>
Material* ...	<u>Siemens Steel</u> <u>Forged</u> <u>Iron.</u> <u>Dia 5 3/4"</u>  <u>Black Forging</u> <u>33.</u> <u>28.80</u> <u>34.00</u> <u>180°</u> <u>24/3/30 to 28/3/30.</u>			
How made ...				
Annealed ...				
Dimensions, Forgings				
Weight, Castings				
Progress on Inspection				
Tests on Standard Test Pieces.				
Tensile Test— Tons per square inch				
Extension per cent				
Cold Bending Test— Angle before fracture				
Dates when Inspected				


PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

N<sup>o</sup> 2641. Shard

LLOYDS  
3470  
R.N.F.  
28-3-30  
© 2021  
19-5-30

Fee (if any chargeable) £ ✓ To be paid at ✓

\* If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.



Lloyd's Register Foundation