

NAME

REPORT

No.

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in hundredths of an inch.

	AMIDSHIP.					FORWARD.					AFT.					REMARKS.
	Original Thickness	Thickness by drilling.		Diminution if any.		Original Thickness	Thickness by drilling.		Diminution if any.		Original Thickness	Thickness by drilling.		Diminution if any.		
		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.	
F	44	38	38	6	6	44	-	31	-	13.	44	44	38.	-	6.	
D	44	R.	38	-	6	44	S.	S	-	-	44	44	44	-	-	R: RENEWED.
C	44	R	R	-	-	44	38.	38	6	6.	44	38.	44	6	-	S-STEALER.
B	44	R.	R	-	-	44	38.	44	6	-	44	38	44	6	-	
A	44	R.	R	-	-	44	44	38	-	6.	44	44	44	-	-	
	44	R		-		44	-	-	-		44	-	-	-	-	
														</		

Drillings at ends to be made in the vicinity of the peak bulkheads.

© 2021

Lloyd's Register
Foundation

012047-012057-0115