

REC'D NEW YORK FEB - 6 1931
 For the information of Surveyors and the Committee only.

Received at _____ Office, _____ 10

Lloyd's Register of Shipping.

(Report on Machinery, No. 317 Port Go)

No. _____ ENGINE FORGINGS OR CASTINGS.

I have to report that the Forgings or ~~Castings~~, as herein described, manufactured by FAIRBANKS MORSE & CO. of BELOIT WIS. U.S.A. for the Engine No. 751354 being constructed by FAIRBANKS, MORSE & CO. of BELOIT, WIS U.S.A. for the Ship No. _____, being built by "PUKEKO" of NAPIER, N.Z. have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to _____

on Forgings or Castings.

Lloyd's
 No. 460
 QB 5-27-30

Paul H Blair

	CRANK SHAFT.	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT.
	FLYWHEEL SHAFT.			SCREW SHAFT.
Material ...	<u>ON STEEL</u>			
Manufacture ...	<u>FORGED</u>			
Heat treated ...	<u>YES</u>			
Dimensions, Forgings				
Dimensions, Castings				
Tests on } Inspection }	<u>TEST SPECIMENS</u>	<u>INSPECTED</u>	<u>FINISHED</u>	
Tests on Standard } Test Pieces. }	<u>MAY 27TH</u>	<u>FORGING</u>	<u>JUNE 9TH 1930</u>	
Strength Test— Tensile strength per square inch	<u>83,400</u>			
Elongation per cent	<u>32%</u>			
Bending Test— Degrees before fracture	<u>180° OK</u>			
Date when Inspected	<u>5-3-30</u> <u>5-27-30</u>			


PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

(if any chargeable) £

To be paid at

Chicago Ill

If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.



© 2021

Lloyd's Register
 Foundation

012508-012513-0075