

BRITISH
 EL'S NAME M.V. MARISIN Max HONOUR. REPORT GENOA No. 77333

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in hundredths of an inch.

TRAKE.	AMIDSHIP.						FORWARD.						AFT.						REMARKS.
	Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.					
		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.				
SSHEER KE	42	40	38	2	4	42	40	38	2	4	40	38	36	2	4				
below						42	37	41	5	1									
STRAKE	L	98	92	96	6	2	53	51	50	2	3	50	44	46	6	4			
ke below	K	84	78	80	6	4	54	50	49	4	5	50	46	45	4	5			
"	J	60	52	52	8	8	49	41	42	8	7	49	40	42	9	7			
"	H	60	46	52	14	8	49	40	43	9	6	47	41	40	6	7			
"	G	60	52	54	8	6	49	46	48	3	1	49	43	45	6	4			
"	F	68	62	64	6	4	66	62	61	4	5	66	59	62	7	4			
"	E	69	60	58	9	11	STEALER.				STEALER.								
"	D	69	62	62	7	7	STEALER.				STEALER.								
"	C	63	68	52	+5	11	66	60	59	6	7	66	58	58	8	8			
"	B	63	46	60	17	3	66	58	58	8	8	50	48	46	2	4			
"	KEEL	96	82		14		76	68		8		76	65		11.				
"																			
"																			
"																			

2021
Lloyds
H. J. Mansfield.
95/5/53

Drillings at ends to be made in the vicinity of the peak bulkheads.

012744-012751-0225