

Page.

15.

Lloyd's Register of Shipping.

RESULTS OF TESTS OF STEEL. SHAFTS.

Made by Messrs. Wm. Beardmore & Co., Ltd. Glasgow.

For Messrs. D. Rowan & Co., Ltd. Eng. No. 963, for Messrs. Lithgows, Ltd. Ship No. 866.

No.	Test No.	No. of Pieces.	Description.	Charge Mark.	Sample No.	dia. Thickness.	Area.	Tons per square inch.	Extension on 3 inches.	% Bend
F.	31-2	2	Crank Pins.			.798	.50	30.0	31	180°
"	33	1	do do			"	"	29.8	32	"
"	34	1	Crank Journal.			"	"	30.0	31	"
"	28-9	2	Coup. Ends.			"	"	30.0	32	"
"	30	1	do do			"	"	29.8	31	"
"	35	1	Crank End.			"	"	29.6	32	"
"	36	1	Conn. Rod.			"	"	29.8	30	"
"	37	1	do do			"	"	30.2	30	"
"	38	1	do do			"	"	30.4	30	"
"	39	1	Prop. Shaft.			"	"	28.8	31	"
"	40	1	Thrust Shaft.			"	"	29.6	32	"
"	41	1	Inter. Shaft.			"	"	30.2	30	"
"	42	1	do do			"	"	29.8	30	"
"	43	1	do do			"	"	29.6	30	"
"	44	1	do do			"	"	30.0	30	"
"	45	1	do do			"	"	29.2	34	"

Chas. S. Porter.

Glasgow. 3/8/1933



© 2021

Lloyd's Register

012888-012897-0240