

For the information of Surveyors and the Committee only.

Received at \_\_\_\_\_ Office, \_\_\_\_\_ 19

# Lloyd's Register of Shipping.

(Report on Machinery, No. 11175 Port Belgian)

## No. F.3624 ENGINE FORGINGS OR CASTINGS.

I have to report that the Forgings or Castings, as herein described, manufactured by Metalropolitan Vickers Electrical Co., Ltd. of Manchester for the Engine, No. \_\_\_\_\_ being constructed by Metalropolitan Vickers Elec. Co., Ltd. of Manchester for the Ship No. \_\_\_\_\_, being built by "CITY OF KIMBERLEY" of \_\_\_\_\_

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to \_\_\_\_\_

on Forgings or Castings.

Arthur J. Anderson  
Manchester, 28.9.33.

Lloyd's  
No. 532  
10-8-33 G.A.

	<del>CRANK SHAFT.</del>	<del>THRUST SHAFT.</del>	<del>INTERMEDIATE SHAFT.</del>	<del>TUBE SHAFT.</del>
	<u>Generator Shaft.</u>			
	<del>FLYWHEEL SHAFT.</del>			<del>SCREW SHAFT.</del>
Material ...	<u>O. 22 In. Steel</u>			
Made ...	<u>Roller</u>			
Heat-treated ...	<u>Yes</u>			
Dimensions, Forgings	<u>✓</u>			
Weight, Castings	<u>✓</u>			
Test on { specimen }	<u>Finished</u>			
Test on Standard Test Pieces.				
Yield Test— lb per square inch	<u>31.9</u>			
Tension per cent	<u>34</u>			
Bending Test— lb before fracture	<u>180</u>			
When Inspected	<u>26.5.33</u>			


PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

Spec. 32 to 34 tens 25% Elongation.

(if any chargeable) £ —

To be paid at —

If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.



© 2021

Lloyd's Register  
Foundation

013449-013453-011