

"Paradise Beach"
 Baltimore, Md.
 First Entry Report No. 11729

**ANKSHAFT PHYSICAL
 TEST REPORT**

SOURCE Wyman - Gordon DATE February 19, 1957
 SPEC. S.A.E. 1050 Mod. HEAT NO. 117832
 PART NO. 4H-7032 MARK RDO
 SPECIMEN DESCRIPTION Tensile specimen cut from mid-radius of 4" Rd. sample.
Sample had been quenched and drawn to indicated hardness.

ANALYSIS:	C	MN	S	P	SI	N	CR
	.51	1.10	.035	.015			.08
P. LBS. PER SQ. IN.	82,000						
S. LBS. PER SQ. IN.	121,750						
ELONG. IN 2 INS.	23.0						
REDUCTION OF AREA	57.4						
HARDNESS	262						

I HEREBY CERTIFY THAT TO THE BEST OF MY KNOWLEDGE AND BELIEF, THE ABOVE REPORT IS TRUE AND CORRECT.

[Signature]
 METALLURGICAL DEPARTMENT

SUBSCRIBED AND SWORN TO BEFORE ME THIS 19th DAY OF Feb. 1957.

[Signature]
 NOTARY PUBLIC

My Commission Expires August 1, 1958

