

For the information of Surveyors and the Committee only.

Received at

Office

11 MAY 1934

# Lloyd's Register of Shipping.

(Report on Vessel No. 1421. Port bdy)

## To 141 SHIP ~~FORGINGS~~ OR CASTINGS.

I have to report that the undermentioned ~~Iron or Steel Forgings or~~ Castings, manufactured by Messrs. Soc. Esp. de Const. Naval of Reinosa for the Vessel No. 66, being built by Messrs. Soc. Esp. de Const. Nav. of Cadix, has been inspected by me as set forth below and found to be, so far as can be seen, sound & free from defects.

Forgings or Castings.

Lloyd's  
No. 35  
1-32 G.D.

G. Dixon.

Bilbao.


	LOWER PART STERN FRAME.	RUDDER FRAME.	STEM.
* ...	<u>Elec. Furn. Steel</u>	/	/
de ...	<u>Cast.</u>		
ns ...	<u>1300 Kgs.</u>		
on Inspection ...	<u>Cast.</u>		
en Inspected ...	<u>10.12.31 &amp; 5.1.32</u>		
ASTINGS.			
Standard Test			
Pieces.			
Test—			
square inch	<u>49.4</u>		
on per cent. ...	<u>31</u>		
ding Test—			
before fracture	<u>180° Good.</u>		
from ground ...	<u>10' - 0"</u>		
ing Test—			
according to Rules	<u>Yes.</u>		
and satisfactory ...			

SKETCHES OF FRAMES SHOWING POSITION AND DESCRIPTION OF WELDS OF FORGINGS.

(if any chargeable) £ :

To be paid at

Iron, state whether scrap or puddled Iron. If of Steel, state whether made on the Open Hearth process.



© 2021

Lloyd's Register  
Foundation

014287-014299-0228

Seamless, lap welded or riveted longitudinal joint. rivetted Material SM Steel Range of tensile strength 41-44 Ks. Working p