

(Received in London Office

Date first visit 17<sup>th</sup> Oct/81 last visit 17<sup>th</sup> Oct/81 No. of Visits 1

The Plates specified in the accompanying copy of Advice Notes were rolled from \_\_\_\_\_ charges. The tensile test has been applied to \_\_\_\_\_ samples as set forth below, and the temper and bending tests to a shear from each plate, with satisfactory results.

No.	Purpose.	Charge Mark.	No. of plates or bars in same charge	Mark on plate and test piece.	Dimensions.			Ultimate Stress.		Exten. in 8 ins.	Remarks.	
					Thickn.	Brdth.	Area.	Total.	Sq. Inch.			
					Ins.	Ins.	Ins.	Tons.	Tons.			%
	7'-6" x 14'-0" x 66" x 1/4"	7258			1740	.76	125	.897	2491	27.7	27	W.J. 23/10/83

W.F.  
23/10/83

Expenses £ : :

£ : .

To be paid by *Messrs. J. W. Besant & Co.* Glasgow  
20/10/83



J. J. Covey  
General Agent  
No 3047

Lloyd's Register  
Foundation

LRF/PUN/BeL52A/81R