

✓ 166x170

Date first visit 2/8/3 last visit 2/8/3 No. of Visits 1

The plates specified in the accompanying copy of Advice Notes were rolled from charges. The tensile test has been applied to 1 samples as set forth below, and the temper and bending tests to samples representative of each plate advised. Satisfactory.

No.	Purpose.	Charge Mark.	No. of plates or bars in same charge	Mark on plate and test piece.	Dimensions.			Ultimate Stress.		Exten. in 8 ins.	Remarks.
					Thickn.	Brdth.	Area.	Total.	Sq. Inch.		
					Ins.	Ins.	Ins.	Tons.	Tons.	%	
1		74307		4030	.775	1.16	.599	27.2	20.2	26.0	

D.G.
6/9/83

© 2021

25/9/83

£ : :

To be paid by *The Manufacturers*

Charles Edwards
Surrey, Lloyd's Register.

© 2021

[6000—18/6/81.]

Edwards
Lloyd's Register,
Glasgow

2/9/13