

HALLSIDE, the

day of

188

Test No.	Charge No.	Piece No.	Order No.	Desn.	DIMENSIONS.			ULTIMATE STRESS.		EXTENSION.			Length or Cross.	REMARKS.
					Bdth.	Thk.	Area.	On Piece.	Per Sq. In.	Length.	Ins.	Per Cent.		
0														
1														
2														
3														
4														
5														
6														
7														
8														
9														
0														
1														
2														
3														
4														
5														
6														
7														
8														
9														

Tests from Harland & Wolff's N^o-213
Stem frame.

{ 1.20 .49 .588 18.9 32.1 23.5% extension in 8"
1.20 .50 .600 19.6 32.6 18.5% " " "

Bent through an angle of 101° without
visible fracture.



© 2019

Lloyd's Register
Foundation

BEL55-0170