


# THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet *Newton* Works, the *28<sup>th</sup>* day of *October* 18*89*

ORDER NO.	QUALITY.	CHARGE NO.	SAMPLE NO.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS.	
				Bth.	Thk.	Area.	Actual Tons.	Per @ " Tons.	% Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per @ " Tons.	Bth.	Thk.	Area.	%		
				Harland and Wolff's Stern Frame N° 228 Ship.																	
				H. P.	1.22	.48	.585	18.8	32.1	20.0											
				H. P.	1.22	.49	.597	19.6	32.8	23.0											
																					
				Bend test bent to 92° without fracture																	
																				Thos. W. Gray Surveyor to Lloyd's Register Glasgow	
BEL 57-0074																					



228

re-report on forgings  
of sternframe

Oct 20 1889

S. J. Hassey  
Belfast Report  
No. 3726

SHIP FORGINGS OR CASTINGS.

(Report on vessel No.

George Griffiths of Bristol and London Shipping



© 2019

Lloyd's Register  
Foundation