

THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet *Newton* Works, the *14th* day of *February* 1890

ORDER NO.	QUALITY.	CHARGE NO.	SAMPLE NO.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS.
				Bth.	Thk.	Area.	Actual Tons.	Per 9" Tons.	% Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per 9" Tons.	Bth.	Thk.	Area.	%	

Messrs Harland & Wolff's Stern Frame for Ship No 231

H.P. 1.21 .47 .568 17.5 30.8 23.0

H.P. " .48 .580 18.3 31.5 23.5

*Thos. H. May
Surveyor to Lloyd's Register
Glasgow.*

*Bend test bent
to 91° without fracture.*



© 2019

Lloyd's Register
Foundation

BEL57-0227

Q4-W

N^o 231

re- Coatings
stern frame

17-2-90

Mississippi
Belfast Report

N^o 3790



© 2019

Lloyd's Register
Foundation