

THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet

Newton



Works, the

3rd

day of

April

1890

ORDER NO.	QUALITY.	CHARGE NO.	SAMPLE NO.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS.
				Bth.	Thk.	Area.	Actual Tons.	Per " Tons.	% Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per " Tons.	Bth.	Thk.	Area.	%	
<i>Messrs Harland & Wolff's Stern Frame for No 235 Ship.</i>																				
<i>H. P.</i>				<i>1.24</i>	<i>.49</i>	<i>.607</i>	<i>19.1</i>	<i>31.4</i>	<i>31.0</i>											
<i>H. P.</i>				<i>1.24</i>	<i>.49</i>	<i>.607</i>	<i>19.1</i>	<i>31.4</i>	<i>21.5</i>											
																				
<i>Bend test bent to 86° without fracture.</i>																				
<i>J. H. May</i> <i>Surveyor to Lloyd's Register</i> <i>Glasgow.</i>																				
																				
© 2021 Lloyd's Register Foundation																				
BELSQ-078																				



© 2021

Lloyd's Register
Foundation

BELSG-078

235

Castings on
Stern Frame

Bel - 5-5-90

"British Crown"
Belfast Report
N^o 3855



© 2021

Lloyd's Register
Foundation