

THE STEEL COMPANY OF SCOTLAND, LIMITED.

Bd 3970.

Test Room Sheet

Newton Works, the 28th. day of October 1890

ORDER No.	QUALITY	CHARGE No.	SAMPLE No.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS.
				Bth.	Thk.	Area.	Actual Tons.	Per $\square$ Tons.	% Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per $\square$ Tons.	Bth.	Thk.	Area.	%	
				1.22	.48	.585	17.3	295	22.0	5"										
<p>Bend test bent to 92° without fracture.</p> <p>Alex<sup>r</sup> Kidd  Pro. L. Wray  Surveyor to Lloyd's Register  Glasgow</p> <p>Harland &amp; Wolff's  2:240.  Cast-steel stem frame.</p>																				



© 2019

Lloyd's Register Foundation

BE259-0043



240

Wm. frame

S. L. C. heath

But Rpt 3970



© 2019

Lloyd's Register  
Foundation