

THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet *Newton* Works, the *17th* day of *March* 189*1*

ORDER No.	QUALITY.	CHARGE No.	SAMPLE No.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS.
				Bth.	Thk.	Area.	Actual Tons.	Per $\frac{3}{4}$ " Tons.	% Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per $\frac{3}{4}$ " Tons.	Bth.	Thk.	Area.	%	

Results of Tensile & Bend Tests for Messrs Harland & Wolff's Stem Piece for H^o 245 Ship.

1.21 .50 .605 19.1 31.5 25.0

1.21 .50 .605 18.7 30.9 15.0

Bend test bent as shown without fracture.

*Thos. W. May
Surveyor to Lloyd's Register
Glasgow.*



© 2019

Lloyd's Register
Foundation

BE459-0178

245

Ship Castings

Stem

31-3-91

Indani

Belfast Report

No 4019



© 2019

Lloyd's Register
Foundation