

THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet

Newton Works, the

3rd day of *July* 1891

ORDER No.	QUALITY	CHARGE No.	SAMPLE No.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS.
				Bth	Thk.	Area.	Actual Tons.	Per $\frac{sq}{Tons}$.	$\frac{in}{8}$ Ins.	$\frac{in}{16}$ Ins.	$\frac{in}{32}$ Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per $\frac{sq}{Tons}$.	Bth	Thk.	Area.	$\frac{in}{16}$	
			1	1.20	.47	.564	17.2	30.5	25.0											
			2	"	.47	.573	17.4	30.3	20.0											

*Bend test bent to 94°
without fracture.*

*Alex^r Kidd
Surveyor to Lloyd's Register
Glasgow*



© 2019

Lloyd's Register
Foundation

BEC59-0205

246
R. Castings on
Boss arms

9-7-91



© 2019

Lloyd's Register
Foundation