

THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet

Newton

Works, the

1st

day of

June

18 91

ORDER No.	QUALITY.	CHARGE No.	SAMPLE No.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS
				Bth.	Thk.	Area.	Actual Tons.	Per \square Tons.	% Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per \square Tons.	Bth.	Thk.	Area.	%	

*Results of tensile & bend tests for Messrs Harland & Wolff
Stern Frame for Ship No 247*

1.22.495 .603 18.6 30.9 24.5

" .53' .671 18.7 27.8 16.5

*Bend test bent as
shown without fracture.*

*Alex^r Widd
Surveyor to Lloyd's Register
Glasgow*



© 2019

Lloyd's Register
Foundation

2007-0007

247

Re. ship forgings
on Stern frame

3-6-91

Bel. First Entry Rpt.

No 4055



© 2019

Lloyd's Register
Foundation