



THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet *Newton* Works, the *21st* day of *April* 1891

ORDER No.	QUALITY.	CHARGE No.	SAMPLE No.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS.
				Bth.	Thk.	Area.	Actual Tons.	Per \square Tons.	$\frac{1}{10}$ Ins.	$\frac{1}{10}$ Ins.	$\frac{1}{10}$ Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per \square Tons.	Bth.	Thk.	Area.	$\frac{1}{10}$	
<i>Results of Tensile and Bend Tests for Messrs Harland & Wolff's Stem for No 247 Ship.</i>																				
				<i>1.22</i>	<i>.47</i>	<i>.573</i>	<i>18.0</i>	<i>31.4</i>	<i>24.5</i>											
				<i>1.22</i>	<i>.48</i>	<i>.585</i>	<i>18.0</i>	<i>30.7</i>	<i>16.5</i>											
																				
<i>Bend test bent as shown without fracture.</i>																				
<i>J.W. May</i> <i>Surveyor to Lloyd's Register</i> <i>Glasgow.</i>																				



© 2019
Lloyd's Register
Foundation

Belbo-0005



© 2019
Lloyd's Register
Foundation

247

Castings on stem.

Apr 27 1891

Bel. First Entry Rpt.

No 4053



© 2019

Lloyd's Register
Foundation