

## Test Room Sheet

Newton Works, the 5<sup>th</sup> day of September 1891

ORDER No.	QUALITY	CHARGE No.	SAMPLE No.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS.
				Bth.	Thk.	Area.	Actual Tons.	Per $\square$ Tons.	% Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per $\square$ Tons.	Bth.	Thk.	Area.	%	
<p><i>Boss. Arms for Messrs. Harland &amp; Wolffs No. 247.</i></p> <p><i>8"</i></p> <p><i>1 1.22 .48 .585 14.0 29.0 29.0</i></p> <p><i>2 " .50 610 14.8 29.1 22.5</i></p>																				
<p><i>Bend test bent to 95° without fracture.</i></p> <p><i>Alex. &amp; Fiddell</i></p> <p><i>Surveyors to Lloyd's Register</i></p> <p><i>Glasgow</i></p> <p><i>5/9/91</i></p>																				



247  
Castings on Ross  
arms

Sept 28 1891

Bel. First Entry Rpt.  
No 4055



© 2019

Lloyd's Register  
Foundation