

# THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet

*Newton*

Works, the

*3<sup>rd</sup>*

day of

*October*


1891

ORDER No.	QUALITY	CHARGE No.	SAMPLE No.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS.
				Bth.	Thk.	Area.	Actual Tons.	Per $\frac{1}{2}$ " Tons.	$\frac{1}{16}$ " Ins.	$\frac{1}{8}$ " Ins.	$\frac{1}{4}$ " Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per $\frac{1}{2}$ " Tons.	Bth.	Thk.	Area.	$\frac{1}{16}$ "	
			(1)	1.22	.50	.610	19.7	32.3	26.5											
			(2)	"	.48	.595	18.2	31.1	25.5											

*Bend test bent as shown without fracture.*

*Alex<sup>r</sup>. Kidd  
Surveyor to Lloyd's Register  
Glasgow*

BE60-0039



© 2019

Lloyd's Register  
Foundation



248 Manitoba  
Castings on Ross  
arms

Oct 9 1891

First Entry

Bel. Rpt. No 4046



© 2019

Lloyd's Register  
Foundation