



Test Room Sheet

Newton Works, the

$1\frac{1}{2}$ day of September 1891

ORDER No.	QUALITY	CHARGE No.	SAMPLE No.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS.
				Bth.	Thk.	Area.	Actual Tons.	Per Tons.	% Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per Tons.	Bth.	Thk.	Area.	%	
Stern Frame for Messrs. Harland & Wolff's No. 249.																				
8"																				
1 1.22.49 .597 18.2 30.4 24.5																				
2 " .48 .585 17.8 30.4 25.5																				
																				
Bend test bent to 97° without fracture																				
Alex ^r Hidd																				
Surveyor to Lloyd's Register																				
Glasgow																				
5/9/91																				



© 2019
Lloyd's Register
Foundation

13660-0069



Lloyd's Register
Foundation

249

Re. Castings on Stern
frame

28 Sept 1891



Mohawk

Bel. Rpt. No. 4094



© 2019

Lloyd's Register
Foundation