

THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet

Newton Works, the

18th day of August 1891

ORDER No.	QUALITY	CHARGE No.	SAMPLE No.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS.
				Bth.	Thk.	Area.	Actual Tons.	Per \square Tons.	% Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per \square Tons.	Bth.	Thk.	Area.	%	

Stem piece for Messrs Harland & Wolffs' No. 249.

8"
1.22.49.59 19.2 32.1 29.5
" .52.634 18.8 29.6 20.0

Bend test bent to 90°
without fracture

Chas. F. Kidd

SURVEYOR TO LLOYD'S REGISTER,
GLASGOW.

18/8/91

RE 60-0076



© 2019

Lloyd's Register
Foundation