


THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet      *Newton* Works, the      22<sup>nd</sup> day of      *October*      1891

ORDER No.	QUALITY	CHARGE No.	SAMPLE No.	SIZE OF SAMPLE.			BREAKING STRAIN.			EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.			REMARKS.	
				Bth.	Thk.	Area.	Actual Tons.	Per $\frac{1}{2}$ Tons.	$\frac{1}{16}$ Ins.	$\frac{1}{16}$ Ins.	$\frac{1}{16}$ Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per $\frac{1}{2}$ Tons.	Bth.	Thk.	Area.	%		
				<i>Boss. Arms for Muzzes. Harland &amp; Wolff's No. 250.</i>																	
				<i>8"</i>																	
				<i>1. 1.22.50.610 18.0 29.5 22.5</i>																	
				<i>2. " . 51.622 18.7 30.0 25.0</i>																	
																					
<i>Bend test bent to 93° without fracture.</i>																					
<i>Alfred. Fiddel</i>																					
SURVEYOR TO LLOYD'S REGISTER, GLASGOW.																					
<i>22/10/91</i>																					



© 2019

Lloyd's Register Foundation

BEL60-0117