

# THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet

*Newton*

Works, the

18th. day of *March*

18 92

ORDER NO.	QUALITY.	CHARGE NO.	SAMPLE NO.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS.
				Bth.	Thk.	Area.	Actual Tons.	Per Tons.	% Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per Tons.	Bth.	Thk.	Area.	%	


*Results of tests made on Stern Frame for Messrs Harland & Wolff N<sup>o</sup> 256.*

*8"*  
 1 1.23 .50 .615 18.5 30.0 27.0  
 2 " .48 .590 17.9 30.3 26.0

*Bend test bent to 90°  
 as shown without  
 fracture.*

*Wm. & Fiddell  
 Surveyors to Lloyd's Register  
 Glasgow*

BE161-0020.1



© 2020

Lloyd's Register  
 Foundation



256

Basting on Stern  
Frame.

22 March 1892

Sagamore

Bel First Entry Rpt  
no 41 92



© 2020

Lloyd's Register  
Foundation