

Test Room Sheet

Newton Works, the

1st day of

June

1892

ORDER NO.	QUALITY.	CHARGE NO.	SAMPLE NO.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS.
				Bth.	Thk.	Area.	Actual Tons.	Per Tons.	% Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per Tons.	Bth.	Thk.	Area.	%	
<p><i>9 Boss. Arms for Messrs. Harland & Wolffs' No 254.</i></p> <p><i>8"</i></p> <p><i>1 1.25 .48 .600 18.2 30.3 21.0</i></p> <p><i>2 . .47 .584 17.8 30.3 17.0</i></p>																				
<p><i>Bend test bent as shown to 93° without fracture</i></p>																				
<p><i>Allex^r Fricke</i></p> <p><i>Surveyor to Lloyd's Register</i></p> <p><i>Glasgow</i></p>																				

257

Basting on Stern Frame

3rd June 1892

Islam

Bel. First Entry Rpt.

No 4195



© 2020

Lloyd's Register
Foundation