



# THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet

Newton Works, the

31st day of March 1892

ORDER NO.	QUALITY.	CHARGE No.	SAMPLE NO.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS.
				Bth.	Thk.	Area.	Actual Tons.	Per Tons. $\square$ "	% Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per Tons. $\square$ "	Bth.	Thk.	Area.	%	
Stern Frame for Messrs. Harland & Wolff's No 257.																				
8"																				
1 1.25 .49 .612 18.9 30.9 16.5																				
2 " .51 .637 20.7 32.5 25.0																				
																				
Bend test bent as shown to 91° without fracture.																				
Alfred Kidd Surveyor to Lloyd's Register Glasgow.																				



© 2020  
Lloyd's Register  
Foundation

BF761-0034.1



© 2020

Lloyd's Register  
Foundation

BF61-0034.1



25<sup>y</sup>

Castings on Stern  
Frame

7<sup>th</sup> April 1892

Islam

Bel First Entry Rpt.

No. 4195



© 2020

Lloyd's Register  
Foundation