

THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet

Newton Works, the

31st. day of March 18 92

ORDER NO.	QUALITY.	CHARGE NO.	SAMPLE NO.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS.
				Bth.	Thk.	Area.	Actual Tons.	Per \square Tons.	% Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per \square Tons.	Bth.	Thk.	Area.	%	

Stem Piece for Messrs. Harland & Wolff's No 257

1 1.25 .53 .662 19.4 29.3 13.0
2 " .52 .650 20.1 30.9 15.0

*Bend test bent to 91° as
Shown without fracture.*

*Alex^r Hirdel
Surveyor to Lloyd's Register
Glasgow*



© 2020

Lloyd's Register
Foundation

BF661-0035

257

Castings on Stem

April 7th 1892

Islam

Bel First Entry Rpt

No. 4195



© 2020

Lloyd's Register
Foundation