


THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet *Newton* Works, the 9th. day of *June* 1893

ORDER No.	QUALITY.	CHARGE No.	SAMPLE No.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS.
				Bth.	Thk.	Area.	Actual Tons.	Per 8" Tons.	% Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per 8" Tons.	Bth.	Thk.	Area.	%	
<i>Rudder (Solid) for Messrs. Harland & Wolffs' No 272</i>																				
																				<i>8"</i>
<i>.87 Dia .594 18.1 30.4 22.0</i>																				
																				
<i>Bend test bent as shown to 96° without fracture</i>																				
<i>Ally Kidd</i>																				
SURVEYOR TO LLOYD'S REGISTER, GLASGOW.																				
<i>12/6/93</i>																				

27/2

basting

Rudder Solid

Sackem

Del First Entry Rpt

No 4309



© 2019

Lloyd's Register
Foundation