

THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet
Newtown Works, the 6th day of February 1893

ORDER NO.	QUALITY.	CHARGE NO.	SAMPLE NO.	SIZE OF SAMPLE.			BREAKING STRAIN.			EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.			REMARKS.
				Bth.	Thk.	Area.	Actual Tons.	Per. sq Tons.	% Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per. sq Tons.	Bth.	Thk.	Area.	%	
				Stern Frame for Messrs. St Andrews Works. No 242.																
				1	2.00	.50	1.00	24.4	24.4	10.0										
				2	1.20	.51	.612	19.0	31.0	20.5										
<div>Bend test - bent as shown to 93° without fracture</div> <div>Wm. Hall Surveyors to Lloyd's Register Glasgow</div>																				



© 2019

Lloyd's Register
Foundation

272

Castings on
Stern Frame

Sachem

Bel First Entry Apt

104309



© 2019

Lloyd's Register
Foundation