

THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet

Newton


Works, the


23rd

day of

January

1893

ORDER No.	QUALITY.	CHARGE No.	SAMPLE No.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS
				Bth.	Thk.	Area.	Actual Tons.	Per $\frac{1}{2}$ " Tons.	$\frac{1}{16}$ " Ins.	$\frac{1}{8}$ " Ins.	$\frac{1}{4}$ " Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per $\frac{1}{2}$ " Tons.	Bth.	Thk.	Area.	$\frac{1}{16}$ "	
Stem-Piece for Messrs Harland & Wolffs' No 242																				
																				8"
1																				1.16 50.580 14.9 30.8 14.0
2																				.51.591 18.2 30.8 15.0
																				
Bend test-bent to 95° as shown without fracture.																				
Alex ^r Kidd Surveyor to Lloyd's Register. Glasgow.																				



© 2019
Lloyd's Register
Foundation

© 2019

Lloyd's Register
Foundation

272

Castings on Stem

25 Janry '93

Sackem

Bel. First Entry Rpt.

No 4309.



© 2019

Lloyd's Register
Foundation